



CLAY BRICKS D. J. KOKKINOGENIS SA  
NATO AVENUE 19300 ASPROPYRGOS

11

EN 771-1

Clay brick with horizontal drilling II, LD, 60X90X190 mm

Compressive Strength: 2.7N/mm<sup>2</sup> (⊥bed face),  
190x90 (Cat. II)

Dimensional tolerances: Cat. Tm

Adhesive strength: ..... 0,15 (N/mm<sup>2</sup>)

Active soluble salts content: .....NPD (SO)

Reactions to fire: Euroclass..... A1

Water absorption: ..... not relevant

Water vapor diffusion coefficient : ..... μ 5/10

Direct airborne sound insulation :

Gross density: .....892.7 Kg/m<sup>3</sup>

Net density: .....1697.7 (Dm) Kg/m<sup>3</sup>

Configuration: As in attached drawing

Equivalent thermal conductivity: 0,47 W/mK (λ<sub>10,drv</sub>)

Durability against freeze-thaw: (NPD)

Dangerous substances: ...none

